

# INSTALLATION GUIDE

## MASONRY

Breathaplasta Universal can be applied directly to brick, block and stone and is compatible with all masonry types. Breathaplasta Universal is a quick and easy lime plaster. It's simple to use and sets within an hour.

### Important notes for use on masonry:

- Ensure the masonry is consolidated. Dub out the masonry if needed – fill holes and level off.
- Mist the surface of the masonry 10-15 mins prior to plaster application to control suction.
- Allow 1 hour to dry per 2mm of plaster thickness.

### Mix

Water required



Add 1 x 18kg bag of Universal to approx. 8 litres of clean water.

### Mix Time



Mix the plaster using a paddle mix for approx. 3 minutes.

### Mist

With water



Mist or brush the masonry surface with clean water to control suction.

### Apply

Two coats



Apply at least 2 coats of Universal. Each coat should be up to 10mm thick.

### Set

Setting time



Setting time per coat of Universal is approx. 45-60 minutes.

### Finish

Use clean trowel



Run a clean trowel over the surface of the plaster for a smooth finish. Use a sponge float for more textured finishes.

## breathAplasta



Good for our buildings



Good for our health



Good for our planet

### Equipment Required:

Breathaplasta Universal, clean water, brush or mister, hawk, trowel and plastering tools.

### Surface preparation:

Consolidate wall to ensure no loose material. Surface should be uniformly flat. Mist the masonry surface with water to help control suction.

### Recommended plaster thickness:

Each coat should be between 2-10 mm thick.  
Up to 20mm max per day.  
Up to 50mm max total thickness.

### Recommended plaster application:

1. Base coat/scratch coat of Universal up to 10mm.
2. Additional coats up to 10mm thick, up to 20mm max per day. Up to 50mm max total thickness.
3. Top coat approx. 2-4mm. Moisten top coat using a fine mist spray bottle to help trowel to a smooth finish.

### Coverage per 18kg Universal bag:

Approx. 5m<sup>2</sup> at 4mm thickness

### Setting time per coat:

Approx. 45 - 60 minutes